



ديكو بروجكت للتجارة
Deco Project Trading

TECHNICAL DATA OF KRONOSWISS

Technical Specification

Test Standard	Test Institute	Test	Results
EN 13329	WKI	Resistance to impact test	Impact Test Category NK 23-31: IC1, NK 32: IC2, NK33: IC3
EN 120	WKI	Externally controlled Formaldehyde Test	E1 HDF
EN 13329	WKI	Resistance to staining	Group 1-2: Level 5, Group 3: Level 4
EN 13329	WKI	Resistance to light	Blue wool scale: not worse than 6, Grey Matter : No worse than 4
EN 13329	WKI	Resistance to burning cigarette	Level 4
EN ISO 9239-1 EN ISO 11925-2 EN 13501-1	MPA	Reaction to Fire	Flame-retardant, Building Class Cfl-s1
EN 13329	WKI	Effect of a moving Furniture coaster	No visible reaction to coaster type O
EN 13329	WKI	Wheelchair Test	No visible changes or damage, as defined in EN 425
DIN 52612	eph	Thermal Conductivity	$\lambda_{10.tr} = 0.17 \text{ W/m.K}$, Suitable for underfloor heating (medium : water)
		Disposal	Disposal as per household waste

Further Information can be found at: www.kronospan.com



Qatar Branch :

28, Yamamah Centre, Salwa Road, Doha, Qatar, Tel.: +974 44502162

Fax: +974 44316153, Mobile: +974 77718762 / 55571106

E-mail : info@decoprojectme.com / decoproject@gmail.com Website : www.decoprojectme.com

